



# WBP - Hybrid Emulsion

## Ryonet

[www.SilkScreeningSupplies.com](http://www.SilkScreeningSupplies.com)

[sales@ryonet.com](mailto:sales@ryonet.com)

1-800-314-6390

## Applications

Diazo sensitized emulsion for Plastisol, Discharge, and Water Based inks. Ideal for use with Phthalate compliant ink systems.

## Physical Properties

- ☀ Red Colored, also available in Clear
- ☀ Virtually pinhole and fish eye free
- ☀ Extremely Durable for long print runs
- ☀ Outstanding resolution and definition
- ☀ 38% solids
- ☀ Superior Solvent resistance to Aerosol Screen Openers

## Handling

Handle under yellow safelight conditions.

## Sensitizing

Mix sensitizer according to the instructions on the bottle. Pour the solution into the emulsion and mix thoroughly. Let the emulsion stand for 2 hours to let the air bubbles release from the emulsion.

## Mesh Preparation

It is important to have a clean dry screen before you apply the emulsion. To achieve this use a good CCI degreaser available from Ryonet.



**Chemical Consultants, Inc.**  
Corona, CA 92880 USA

## Coating Procedure

Use a clean coating trough that has a smooth edge without nicks or burrs. Coating environment should be in a clean light safe area with 65% humidity level.

1. Apply one or two coats of emulsion to the print side.
2. Reverse the screen and apply one or two coats to the squeegee side.

To achieve user specific results, additional coats may be used.

## Drying

Dry the screen in a horizontal position with the print side down in a clean dry room. Follow these guidelines to ensure complete drying:

- ☀ 86° to 104° F (30° to 40° C)
- ☀ 30% to 50% relative humidity
- ☀ Good air circulation

\*To achieve the desired humidity levels the use of a dehumidifier is recommended.


## Exposure

For best results use an exposure calculator to determine the exact exposure time. Proper exposure is determined by a number of conditions such as clean film positives, mesh color, emulsion type, emulsion thickness and exposure unit type.

APPROXIMATE EXPOSURE TIMES			
MESH	UV BLACKLIGHT	SECONDS	
86	260-280	260-280	110
110	250-270	250-270	75
200	240-260	240-260	60
230	230-250	230-250	45
305	230-240	230-240	40
		1K	5K

METAL HALIDE LAMP

Note: Above times are based on using a screen coated 2/2.



Step 1.  
Print Side



Step 2.  
Squeegee Side

## Washout

Gently spray both sides of the screen with water. Wait a moment to allow the emulsion to soften. Wash print side of the screen until the image is fully open. Rinse both sides thoroughly and dry. A vacuum can be used to accelerate drying.

## Reclaiming

Removing the emulsion is simple with one of CCI's ready to use or concentrated emulsion removers.

## Storage

Store the emulsion in a cool dry place. Unopened emulsion has a shelf life of one year when stored properly. Coated screens will last up to 30 days with good results when stored correctly.

- ☀ 59° to 77° F (15° to 25° C)
- ☀ 40% to 60% humidity

Reorder Supplies at:  
[www.SilkScreeningSupplies.com](http://www.SilkScreeningSupplies.com)